



POLYURETHANE SIKA PRE-TREATMENT CHART

FOR 1-COMPONENT POLYURETHANES – Sikaflex®-100 AND -200 SERIES

UTILIZATION OF SIKA PRE-TREATMENT CHART

The information about the pre-treatment of surfaces in this document serves as a guideline only and must be verified by tests on original substrates. Project specific pre-treatment recommendations, based on laboratory tests, are available from Sika upon request. Always consult additional information.

GENERAL RECOMMENDATIONS FOR Sikaflex®-100 AND -200 SERIES


PRECONDITION:

Surfaces have to be clean, dry and free of oil, grease, dust and loose particles. Depending on the nature of soiling, Sika® Remover-208, Sika® Cleaner P or another suitable cleaning solution may be used. For substrates that are prone to oxidation and/or have a weak surface layer it might be necessary to abrade the surface down to sound material. Verify compatibility with cleaning products.

Levels	Description
1	<ul style="list-style-type: none"> General sealing applications, small components with low level of stress exposure Non-structural interior bonding applications, no exposure to temperature extremes, no contact with water
2	<ul style="list-style-type: none"> Sealing applications involving large components where higher joint movements are to be expected Interior and exterior bonding applications under normal environmental conditions
3	<ul style="list-style-type: none"> Other applications, not covered under Level 1 and 2, where additional requirements are specified Serial application

Substrate	EN*	1			2			3
		Mechanical	Adhesion Promoter / Cleaner	Primer	Mechanical	Adhesion Promoter	Primer	
Aluminum (AlMg3, AlMgSi1 and similar)	1	AP-C	SA-100		AP-C	SA-205	SP-204 N	
		AP-C		SP-207	AP-C		SP-207	
Aluminum (anodized)	2		SA-100			SA-205	SP-204 N	
				SP-207	AP-C		SP-207	
Steel (mild)	3		SA-205	SP-204 N	AP-C	SA-205	SP-204 N	
			SA-100	SP-206 GP	AP-C		SP-207	
Steel (stainless)	4		SA-100		AP-C	SA-205	SP-204 N	
				SP-207	AP-C		SP-207	
Steel (hot-dip galvanized, electrogalvanized)	5		SA-205		AP-C	SA-205	SP-204 N	
				SP-207	AP-C		SP-207	
Non-ferrous metals (copper, brass, bronze,...)	6	AP-C	SA-205	SP-210	AP-C	SA-205	SP-210	
2-Component top coat, water- and solvent based (PUR, acrylic)	7		SA-100				SP-207	
				SP-207		SA-100	SP-206 GP	
Powder coat (Polyester (PES), EP/PES)	7		SA-100		AP-C		SP-207	
				SP-207	AP-C	SA-100	SP-206 GP	
2-Component paint primer, water- and solvent based (PUR, acrylic, epoxy)	7		SA-100				SP-207	
				SP-207		SA-100	SP-206 GP	
Cathode dip coating (e-coating)	7		SCP				SP-207	
			SA-100			SA-100		
Coil coating, mainly Polyester	8		SA-205		AP-C	SA-205		
			SCA			SCA	SP-206 GP	
FRP (unsaturated polyester) gelcoat side or SMC	9		SA-100		AP-C	SA-100		
				SP-207			SP-207	
FRP (unsaturated polyester) lay-up side	9	AP-C		SP-207	GR-V		SP-207	
		AP-C	SA-100	SP-206 GP	GR-V	SA-205	SP-215	
FRP (Epoxy-matrix), CFRP	10	AP-C		SP-207	AP-C		SP-207	
		AP-C	SA-100	SP-206 GP	AP-C	SA-100	SP-206 GP	
ABS	11			SP-209 D		SA-100	SP-209 D	
				SP-206 GP		SA-100	SP-206 GP	
Hard PVC	11			SP-215		SA-205	SP-215	
				SP-207			SP-207	
PMMA / PC (without anti scratch coating)	12			SP-209 D	AP-C		SP-209 D	
				SP-207	AP-C		SP-207	
Glass	13			SP-207			SP-207	
			SA-100			SA-100		
Ceramic screen print	13			SP-207			SP-207	
			SA-100			SA-100		
Wood / Plywood	14						SP-215	

* EN = Explanatory notes see page 4.
Note: Not all products available globally

 Recommended process
 Alternative process

CONTACT SIKA TECHNICAL DEPARTMENT INDUSTRY

PRODUCT DATA AND ABBREVIATIONS

The following product information is an abbreviated version of the current Product Data Sheets.

Sika® Aktivator	-100	-205	Sika® Coating Aktivator*
Color of container cap	orange	yellow	white
Color of product	colorless to slight yellow	colorless, clear	colorless to slight yellow
Type of product	Adhesion promoter		
Application temperature	The general range is 10 – 35 °C. For specific values always refer to the most recent Product Data Sheet.		
Application	Wipe with a clean and lint-free paper towel (Sika Aktivator®-100 wipe on / wipe off application is required)		
Consumption	Approximately 20 ml/m ² (depending on application method).		
Flash-off time (23 °C / 50 % r.h.)	The minimal range of the flash-off time varies from 10 to 30 minutes depending on product, substrate and climatic conditions. For specific values always refer to the most recent Product Data Sheet.		

Sika® Primer	-204 N*	-206 G+P	-207	-209 D	-210	-215
Color of container cap	light blue	black	black	green	grey	dark blue
Color of product	opaque yellow	black	black	black	transparent, yellowish	transparent, yellowish
Type of product	Primer					
Application temperature	The general range is 10 – 35 °C. For specific values always refer to the most recent Product Data Sheet.					
Preparation for use	Shake bottle vigorously until the mixing balls rattle freely. Then continue shaking for an additional minute.				n.a.	
Application	Brush / felt / foam applicator					
Consumption	Approximately 50 ml/m ² (depending on application method and substrate porosity).					
Flash-off time (23 °C / 50 % r.h.)	The minimal range of the flash-off time varies from 10 to 30 minutes depending on product, substrate and climatic conditions. For specific values always refer to the most recent Product Data Sheet.					

Notice: Sika® activators and primers are moisture reactive systems. In order to maintain product quality it is important to reseal the container immediately after use. With frequent use i.e. opening and closing several times, it is recommend disposing of the product one month after the first opening. With infrequent use, it is recommend disposing of the product 2 months after opening.

When selecting a foam applicator, the solvent resistance must be considered. Suitable products include Sika® Power Clean Aid or melamine foam Basotect from BASF.

Abbreviation	Product/Explanation
AP-C	Abrasive Pad, very fine (e.g. from Sia or 3M) followed by cleaning step, dry wipe or SCP
GR-V	Grinding (60 – 80 grit) and vacuum cleaning
SCP	Sika® Cleaner P*
SA-100	Sika® Aktivator-100
SA-205	Sika® Aktivator-205
SCA	Sika® Coating Aktivator*
SP-204 N	Sika® Primer-204 N*
SP-206 GP	Sika® Primer-206 G+P
SP-207	Sika® Primer-207
SP-209 D	Sika® Primer-209 D
SP-210	Sika® Primer-210
SP-215	Sika® Primer-215

* Not available in U.S.A.

Always consult additional information, such as General Guidelines "Bonding and Sealing with Sikaflex®", current Product Data Sheets, Safety Data Sheets, additional Product- and Technical Information, etc. prior to use of the products. Project oriented solutions are documented in Technical Service reports. These solutions can vary from the table opposite and take priority over the general recommendations provided in this Pre-Treatment Chart.

LEGAL DISCLAIMER

This information only applies to the application(s) and product(s) expressly referred to herein and is based on laboratory tests which do not replace practical tests. In case of changes in the parameters of the application such as changes in substrates etc., or in case of a different application, testing is required prior to using Sika products. The information contained in this document(s), including but not limited to any recommendations regarding the use and application of Sika Corporation ("Sika") product(s), is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. The information contained in this document(s) is valid only for the applications and uses of Sika product(s) described herein. Any deviation from any of the instructions, uses, applications and recommendations contained in this document(s) regarding the Sika product(s) will void any Sika Warranty. The user of the Sika product(s) must test each product for suitability for the intended application and purpose. The user of Sika product(s) must always read and follow the warnings and instructions for each product on the current Product Data Sheet, product label and Safety Data Sheets prior to product use. All sales of Sika product(s) are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800. Product Data Sheet(s) and Safety Data Sheet(s) are available at www.sikausa.com or at TSMH@sika-corp.com. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet.

EXPLANATORY NOTES ON SUBSTRATE PREPARATION AND TREATMENT

1. Aluminum

Alloys containing magnesium or silicon may form an unstable layer on the surface. This layer must be removed with a very fine abrasive pad.

2. Aluminum, anodized

For aluminum that has been surface treated, e.g. chromated, anodized or coated, a simple pre-treatment is usually sufficient. Due to the wide variety of anodizing treatments it is necessary to run preliminary tests to check for satisfactory adhesion.

3. Steel, mild

Depending on the exposure conditions, steel is subject to corrosion. Sika primers, which are applied to the surface in a very thin layer, do not provide corrosion protection as such, see also item General Information.

4. Steel, stainless

The terms "stainless steel" and "special steel" encompass a whole group with an important influence on the adhesion behavior. Adhesion can be improved by a prior scuffing step with a very fine abrasive pad.

5. Steel, hot-dip galvanized, electrogalvanized

The surface composition of hot-dip components is not uniform. It is therefore necessary to carry out periodic adhesion checks. Oiled zinc coated steel has to be degreased prior to use. In case of electrogalvanizing the substrate is prepared to a controlled specification and the composition of the surface layer is more or less uniform throughout. Do not use abrasives on electrogalvanized steel.

6. Non-ferrous metals

Metals like brass, copper and bronze are prone to interact with the sealant or adhesive. Therefore it is recommended to contact Sika for advice prior to use.

7. Surface coatings, paint finishes

As a general rule, successful bonding with Sikaflex® products is expected with the following paint systems: cathoretic immersion coatings, powder coatings, epoxy or polyurethane paints. When using the following paint sys-

tems: polyvinyl butyral or epoxy resin ester, cohesion is often higher than adhesion to the substrate. Caution: the presence of paint additives may adversely affect adhesion to the paint surface. Certain coatings can be negatively influenced by weathering. Therefore they have to be protected against UV-light and other aging sources prior to bonding.

8. Coil coating

Coil coating is a process which is defined in EN 10169: 2010. It is the process for coating metal coils. Available coatings include polyesters, plastisols, polyurethanes, polyvinylidene fluorides (PVDF), epoxies. Due to the wide variety of coil coatings, it is necessary to run preliminary tests to check for satisfactory adhesion.

9. FRP (fiber reinforced plastic)

These materials consist for the most part of thermosetting plastics derived from unsaturated polyester, less commonly from epoxy vinyl ester or phenol formaldehyde resins. Newly manufactured components have not yet attained full cure, and as such are subject to further shrinkage following their removal from the mould. For this reason only aged or tempered FRP mouldings should be selected for adhesive bonding. The smooth side (gel coat side) may be contaminated by mould release agents which will adversely affect adhesion. The surface of the rough reverse side, which is exposed to the air during manufacturing has to be abraded thoroughly prior to additional surface preparation. Transparent or translucent FRP must follow the current UV-rules, see General Information.

10. CFRP

(Carbon-fiber-reinforced polymer)

These materials are plastics which contain carbon fibers. The binding polymer is often a thermoset resin such as epoxy, but other thermoset or thermoplastic polymers such as polyester, vinyl ester or nylon are sometimes used. The properties of the final CFRP product can also be affected by the type of additives introduced to the binding matrix (resin).

11. Plastics

Some plastics require special physico-chemical treatment before they can be successfully bonded (flame treatment or plasma treatment in combination with chemical pre-treatment). Polypropylene and Polyethylene are two examples. With many plastic blends it is impossible to give specific guidance due to the potential variety of components and internal/external release agents they contain. Some engineered plastics such as ABS, PMMA and PC may contain substances which can be dissolved by the solvents of that are part of the Sika®Primer formulation, which can then in some cases lead to issues with adhesion. Thermoplastics are subject to a risk of stress cracking. Thermally formed components must be destressed prior to adhesive bonding process. For transparent or translucent plastics see General Information on this page.

12. PMMA/PC

Scratch resistant coating on PMMA or PC must be removed in the bonding area with sand paper (120 grit) and pre-treated as defined for non-coated substrates. Note that this last step may impair the mechanical properties of the PMMA/PC. Contact Sika for solutions without removal of the coating. See also further item 11 and consider always the UV-rules mentioned under "Transparent or translucent substrates" and ESC under item General Information.

13. Glass/Ceramic screen print

Due to production, some windscreens may have silicone contaminated ceramic screen print or glass. It can be removed by using Sika® Power Clean Aid.

14. Phenolic film faces plywood

These are waterproof plywood panels with a yellow or brown film facing. The surface preparation is the same as for paints and coatings. In some cases it could be necessary to grind the surface down to the wood and pre-treat it as such.

GENERAL INFORMATION

Transparent or translucent substrates

With transparent or translucent substrates where the bonded surface is exposed to direct sunlight through the transparent or translucent layer, some form of UV barrier must be incorporated to shield the adhesive bond. This may consist of an opaque cover strip, an optically dense screen printed border or a black primer for semi-transparent substrates such as translucent FRP or screen prints. Due to the high UV exposure for exterior applications the sole use of black primers for UV protection is not sufficient. For interior applications and where the bondline is occasionally exposed to UV-light, a sole black primer for UV protection may be sufficient. Contact Technical Department of Sika Industry.

Corrosion protection

All listed pre-treatment products in this chart are not designed to give comprehensive corrosion protection. In most cases primer layers protect the surface to a certain degree. Whether or not this protection is sufficient for specific processes is at the customers sole discretion.

EPDM/SBR


Rubbers can be made from natural caoutchouc or are produced artificially. Therefore nearly endless combinations are possible. For this reason each type of rubber has to be tested separately.

ESC

At present environmental stress cracking (ESC) is one of the most common causes of unexpected brittle failure of thermoplastics, especially amorphous polymers. Key parameters to trigger ESC are: stress, liquid chemicals, environmental exposure. Each bonding process must be verified.

Protective layer

Substrate surfaces with high variability like galvanization, anodization, coil coating, varnishing, finishing must be subjected to periodic inspections.



Our most current General Sales Conditions shall apply. Consult the most current local Product Data Sheet prior to any use.

SIKA CORPORATION

30800 Stephenson Highway
Madison Heights, MI 48071
U.S.A.
tmsh@us.sika.com
www.sika.com

BUILDING TRUST

